

Premium Additive Anti-Slip R10

Technical Data Sheet
February 2020
Page 1/2



- » additive for our SAICOS Premium Hardwax-Oil
- » suitable for ultramatt, matt, satin matt and high gloss
- » to increase the anti-slip property – R 10

Eigenschaften: An improved anti-slip property can be achieved with the *additive Anti-Slip R10*.

Article number:

3240 colourless for 0,75 can
3240 colourless for 2,5 can

Fields of application:

For all interior wood floors: Parquet, hardwood floors, multi-layer flooring, veneer floors...etc. particularly suitable for special surfaces like stairs, stair heads or in objects e.g. old people's homes.

Preparation: Switch off the underfloor heating 36 h before application. Switch it back on 24 h after applying the last coat. Pour the *additive Anti-Slip R10* in the *Premium Hardwax-Oil* can, stir well – do not thin. Wood surface must be dry and clean (max. moisture content 12 %). Any paints and varnishes must be removed (final sanding grain 120-150). Remove dust thoroughly. Previously oil- or wax-treated surfaces do not require sanding (cleaning with *Ecoline Magic Cleaner*) except wood which is strongly greyed or worn.

Processing: Apply with SAICOS Oil / Wax-Roller

Tip: Do not pour SAICOS Premium Hardwax-Oil directly on the surface, rather work with a Paint Tray.

Note: The quantity in the additive cans fit the particular can size 0,75 L and 2,5 L. Only use one additive per can.

Important Note: We recommend SAICOS Ground Oil Extra Thin as first coat for floors made of hardwoods / exotic woods (European and oversea hardwoods/ exotic woods) and commonly known woods such as Smoked Oak, Meranti, Wengé, Merbau, Jatoba and Ipé. Please see technical data sheet.

Number of coats:

For untreated floors: 2 coats (primer unnecessary). Apply thinly and evenly. Do not use the *additive Anti-Slip R10* only as a final coating. Always apply the *additive Anti-Slip R10* two times.

Renovation: 1 coat usually sufficient.

Best processing temperature: between 8 °C and 35 °C

Coverage per liter: approx. 14 m² (2 coats)

Coverage depends on wood species and surface structure.

Drying time: Min. 3 - 5 hours (depending on temperature and air humidity). Dustdry after approx. 2 hours. Full curing of the surface after approx. 4 - 5 days. Oxidative drying – provide open windows during and after processing to reach a good air circulation.

Easy maintenance:

Cleaning and maintaining: Daily cleaning with mop, duster or vacuum cleaner. Can be mopped damply (*Ecoline Wash Care*). Refreshing care and cleaning with SAICOS Wax Care.

Intensive Cleaning: We recommend our *Ecoline Magic Cleaner*.

Cleaning of tools: with SAICOS Brush Cleaner.

Storage: 3 months

Safety Instructions – First Aid:

Keep out of the reach of children. Do not fill into food, beverage or other containers used for foodstuffs. Wash out any product-soaked rags immediately or store in an airtight container (danger of combustion). The dried coating is normally inflammable acc. to EURO norm EN 13501 (DIN 4102 B2). Causes serious eye irritation. Wash hands thoroughly after handling. Wear protective gloves and eye / face protection. **IF IN EYES:** Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. If eye irritation persists: Get medical advice/attention.

EU limit for two component coatings (cat. A/j): 500 g/l (2010).

SAICOS Premium Hardwax Oil with the *additive Anti-Slip R10* contains max. 500 g/l VOC.

Premium Additive Anti-Slip R10

Technical Data Sheet

February 2020

Page 2/2



Our application advice is provided to the best of our knowledge and based on experiments, however, applies only as a non-binding recommendation and does not exempt you from testing the products supplied by us as to their suitability for the intended purpose. Since the application and processing of the products is beyond our control, the responsibility rests solely with the user. With publishing a new technical data sheet the previous loses its validity.

SAICOS COLOUR GmbH

Carl-Zeiss-Str. 3

D-48336 Sassenberg

☎ +49 2583 3037-0

📠 +49 2583 3037-10

✉ info@saicos.de

www.saicos.de